

CR – 25 HIGH BUILD CHLORINATED RUBBER PAINT SYSTEM.

SURFACE PREPARATIONS: The Concrete surface to be painted should be Dry, free from dust, dirt and grease as well the Drummy surface. Hard Broom / Wire Brush should use to clear the surface.

Generally Wax based Concrete Curing Compounds are used in the Concrete floors – in this situation please use White spirit / Mineral Turpentine and scorn's sponge to rub clean the surface to be painted. Allow to dry for 10-12hours. It is very essential to remove Wax from the surface otherwise the adhesion of paint will not be good.

PAINT APPLICATION

1ST Coat – On clean concrete surface apply one Coat of CR-25 after thinning with thinner TO 6.01 20% Vol to act as primer and get absorbed in the surface can be applied by Brushed, Roller or spray. **Allow to dry for 4-6hours.**

2nd Coat – Mix the supplied aggregates in paint and adjust the consistency suitable for application with TO 6.01. Apply evenly so as not to move aggregates with Brush or Roller. **Allow to dry for 6-8hours**

3rd Coat – Mix Thinner & Aggregates as above. Apply the Coat in direction Perpendicular to 2nd coat in order to have the uniform deposition of aggregates on Court. **Allow to dry for 6-8hours.**

Once the paint has dried the desired court lines can be marked in white or yellow colours of same paint.

THEORETICAL COVERAGE	6.sqm/litre Practical coverage may depend upon on surface profile, method of application and weather conditions.
DRYING TIME	Touch dry approx. 30-35 minutes Hard dry : 24 hours
METHOD OF APPLICATION	Brush, Roller or Spray
THINNING & CLEAN UP	Thinner TO 601