

PACIFIC ELASTOMERIC WALL COATING EWC – 200

Pacific EWC – 200 is an Acrylic Membrane incorporating the recent advances in the Acrylic Polymer and Paint technology. Shows significant advances in the areas of film build, adhesion, Penetration application and durability.

TYPICAL USES

- Concrete Blocks
- Concrete Surfaces
- Fibre Reinforced Cement
- Exterior / Interior

PHYSICAL PROPERTIES

Vehicle Type	Pure Acrylic
Pigmentation	Titanium Dioxide, Minerals and Fibre Reinforcement
Solvent	Water
Finish	Egg Shell, Very Fine Texture
Colours	Whites, Neutrals and BS 5252 Range
Dry Time	1 hour at 25°C
Recoat	4 hours
Primer	Required depending on surface
Theoretical Coverage	1 st Coat 4-5sq.m/l 2 nd Coat 6.5-7sq.m/l
Dry Film Thickness	2 Coats 180 micron
Usual No. of Coats	2, Blockwork – 3
Abrasion Resistance	Very Good
Chemical Resistance	Very Good
Heat Resistance	Thermoplastic
Solvent Resistance	Good
Toxicity	No added Lead or Chromate
Durability	Excellent
Thinning & Clean up	Do not thin, clean up with Water
Pack Size	4 litre & 20Litre

PERFORMANCE

1. Remarkable ease of application.
2. Superior void & crack filling properties
3. Excellent Ultraviolet resistance & Durability
4. Superb resistance to dirt pick up for attractive appearance

LIMITATIONS

1. Old, Weathered Concrete would require conditioning with special sealer.
2. Do not apply at temperature below 10°C or when it is liable to drop below 10°C during the drying period.
3. NOT designed to be used under Pounded Water.
4. Do not apply during Rain or when it is likely to rain.

