

# PACIFIC PREMIUM 100% ACRYLIC ROOF GLOSS

## PREMIUM EXTERIOR FINISH

### PRODUCT DESCRIPTION

A high quality 100% emulsion water based gloss paint, easy to apply and with excellent durability provides repainting cycles of up to 10years.

### AREAS OF APPLICATION

Direct Application

Concrete/ Plaster, Fibrous cement sheeting, Stucco / Rough coat, concrete blocks, brick work, Galvanized Iron Roofing and cladding, weatherboards. After priming timber.

### TECHNICAL DATA

<b>COLOUR RANGE</b>	White & Tint bases can be machine tinted to colours shown in colour chart. Special colours made to orders.
<b>GLOSS LEVEL OF 60C HEAD</b>	70-85%
<b>SOLVENT RESISTANCE</b>	Being thermoplastic film sensitive towards alcohol & aromatic hydrocarbons.
<b>TOXICITY</b>	Dry Film is non-toxic
<b>THINNING &amp; CLEAN UP</b>	Use water for cleaning & Thinning if required.
<b>COVERAGE</b>	16sq.m/litre per coat. Practical coverage may depend on surface profile, method of application and weather condition. Two coats of finishing are recommended.
<b>DRYING TIME (at 25 C &amp; RH 60%)</b>	Touch dry – 30minutes
<b>RECOAT TIME</b>	4-6hours
<b>PACKS AVAILABLE</b>	20L, 10L, 4L, 1L

### APPLICATION

<b>METHOD OF APPLICATION</b>	Brush, Roller or Spray
<b>SURFACE PREPARATION</b>	<ol style="list-style-type: none"><li>1) Remove all dust, dirt, grease, loose and flaking paint by thoroughly cleaning the surface. In some mould or fungus is there on surface then treat with Antifungus solution.</li><li>2) Apply appropriate primer or undercoat.</li></ol>
<b>APPLICATION</b>	Stir the contents in the can thoroughly before and during use, with a broad flat stimer, using an upward lifting action. Apply uniformly from the container. Keep in mind the drying time between coats. On very hot days little bit of thinner (water) could be used for ease of application.
<b>FLAMMABILITY &amp; TRANSPORT INFORMATION</b>	Non-Flammable
<b>SAFETY &amp; PRECAUTIONS</b>	Do not apply at temperature below 10 C. Provide adequate ventilation during use. Keep out of reach of children. Check cross cut adhesion of old paints before repainting In normal condition a week's curing is required to develop full hardness & resistance properties.